

BASIC LOC PLUS

1. Product description

1.1. Format	1380 x 193 x 7 mm
1.2. Packing	9 boards each pack = 2,397 m ²
1.3. Technical description	Three-dimensional interlaced melamine resin Melamine resin, printed decor
- Surface	
- Decor	HDF High Density Fiberboard
- Core layer	Three-dimensional interlaced melamine resin
- Balance film	
1.4. Installation	Mechanical locking system, Clic-System – much easier to install , up to 50% quicker to install (against other clic systems). Floating installation according to the installation description
1.5. Classification	ISO 10874 class 23 : heavy domestic use class 31 : moderate commercial use according EN 15468 EN 14041 CE – Mark
1.6. Fire classification	EN 13501 C _{fl} – s1 (Hardly inflammable ~ B1) E1 lower than 0,05 ppm
1.7. Emission	Technical class DS
1.8. Slip resistance	Thermal resistance according to DIN EN 12667 R= 0,056 [(m ² * K)/W]
1.9. Thermal conductivity	

BASIC LOC PLUS

	Characteristic	Requirements	Unit	Testmethod
1.	Sampling			EN 13329
2.	Thickness	7	mm	EN 13329
3.	Level of use	21 - 31		EN 13329
4.	Wear resistance	AC3		EN 13329
5.	Impact resistance	small Ball ≥ 10 mm big Ball ≥ 500 mm		EN 17368d annex H
6.	Thickness swelling 24h	≤ 18	%	ISO 24336
7.	Resistance to staining	5,g. 1-2 4,g. 3		EN 438-2
8.	Internal bond	$> 1,2$	N/mm ²	EN 319
9.	Surface soundness	$> 1,5$	N/mm ²	EN 311
10.	Locking strength	FI 0,2 ≥ 1 Fs 0,2 ≥ 2	kN/m	ISO 24334
11.	Surface layer width	$\pm 0,1$	mm	EN 13329
12.	Surface layer length	$\pm 0,3$	mm	EN 13329
13.	Squareness	max 0,2	mm	EN 13329
14.	Surface layer straightness	$< 0,3$	mm/m	EN 13329
15.	Height difference between elements	max 0,15	mm	EN 13329
16.	Openings between elements	max 0,2	mm	EN 13329
17.	Formaldehyd content	< 0.05	ppm	EN 717-1

Erstellt (Datum, Unterschrift) QS	Geprüft und Freigegeben (Datum, Unterschrift) 01.07.2023 N. Bublies	
---	---	--