

EXQUISIT

1. Product description

1.1.Format 1380 x 193 x 8 mm (V –Joint 2/4)

1.2.Packing 8 boards each pack = 2,131 m²

1.3.Technical description

- Surface Three-dimensional interlaced melamine resin
- Decor Melamine resin impregnated printed paper
- Core layer HDF High Density Fiberboard
- Balance film Melamine resin impregnated paper

1.4. Installation Mechanical looking system, Clic-System – much easier to install , up to 50% quicker to install (against other clic systems). Floating installation according to the installation description .

1.5.Classification ISO 10874 class 23 : heavy domestic use
class 32 : general

commercial use EN 14041 CE –

Mark

1.6.Fire classification EN 13501 C fl – s1 (Hardly inflammable ~ B1)

1.7.Emission E1 lower than 0,05 ppm

1.8.Slip resistance Technical class DS

1.9.Thermal conductivity Thermal resistance according to DIN EN 12667 R= 0,0587 [(m² * K)/W] With Sound Design Thermal resistance according to DIN EN 12667 R= 0,0690 [(m² * K)/W]

Exquisit

	Characteristic	Requirements	Unit	Testmethod
1.	Sampling			EN 13329
2.	Thickness	8 Or 8mm +1	mm	EN 13329
3.	Level of use	21 - 32		EN 13329
4.	Wear resistance	AC4		EN 13329
5.	Impact resistance	small Ball ≥ 35 mm big Ball ≥ 750 mm		EN 17368d annexe H
6.	Thickness swelling 24h	≤ 18	%	ISO 24336
7.	Resistance to staining	5,g. 1-2 4,g. 3		EN 438-2
8.	Internal bond	$> 1,2$	N/mm ²	EN 319
9.	Surface soundness	$> 1,5$	N/mm ²	EN 311
10.	Locking strength	FI 0,2 ≥ 1 Fs 0,2 ≥ 2	kN/m	ISO 24334
11.	Surface layer width	$\pm 0,1$	mm	EN 13329
12.	Surface layer length	$\pm 0,3$	mm	EN 13329
13.	Squareness	max 0,2	mm	EN 13329
14.	Surface layer straightness	$< 0,3$	mm/m	EN 13329
15.	Height difference between elements	max 0,15	mm	EN 13329
16.	Openings between elements	max 0,2	mm	EN 13329
17.	Formaldehyd content	< 0.05	ppm	EN 717-1

Erstellt (Datum, Unterschrift) QS	Geprüft und Freigegeben (Datum, Unterschrift) 30.01.17 Schmaltz	
---	---	--