



1.1. Format	1845 x 244 x 10 mm
1.2. Packing	4 boards each pack = 1,80 m²
1.3. Technical description	
- Surface	Three-dimensional interlaced melamine resin
- Decor	Melamine resin impregnated printed paper
- Core layer	HDF High Density Fiberboard
- Balance film	Melamine resin impregnated paper
1.4. Installation	Mechanical locking system, Clic-System – much easier to install , up to 50% quicker to install (against other clic systems). Floating installation according to the installation description .
1.5. Classification	ISO 10874 class 23 : heavy domestic use class 33 : heavy commercial use
	EN 14041 CE – Mark
1.6. Fire classification	EN 13501 C fl – s1 (Hardly inflammable ~ B1)
1.7. Emission	E1 lower than 0,05 ppm
1.8. Slip resistance	Technical class DS
1.9. Thermal conductivity	Thermal resistance according to DIN EN 12667 R= 0,084 [(m² * K)/W]

Mammut Plus

	Characteristic	Requirements	Unit	Testmethod
1.	Sampling			EN 13329
2.	Thickness	10	mm	EN 13329
3.	Level of use	21 - 33		EN 13329
4.	Wear resistance	AC5		EN 13329
5.	Impact resistance	small Ball ≥ 70 mm big Ball ≥ 1000 mm		EN 17368d annex H
6.	Thickness swelling 24h	≤ 10	%	ISO 24336
7.	Resistance to staining	5,g. 1-2 4,g. 3		EN 438-2
8.	Internal bond	$> 1,2$	N/mm ²	EN 319
9.	Surface soundness	$> 1,5$	N/mm ²	EN 311
10.	Locking strength	FI 0,2 ≥ 1 Fs 0,2 ≥ 2	kN/m	ISO 24334
11.	Surface layer width	$\pm 0,1$	mm	EN 13329
12.	Surface layer length	$\pm 0,3$	mm	EN 13329
13.	Squareness	max 0,2	mm	EN 13329
14.	Surface layer straightness	$< 0,3$	mm/m	EN 13329
15.	Height difference between elements	max 0,15	mm	EN 13329
16.	Openings between elements	max 0,2	mm	EN 13329
17.	Formaldehyd content	<0.05	ppm	EN 717-1

Erstellt (Datum, Unterschrift) QS	Geprüft und Freigegeben (Datum, Unterschrift) 01.07.2023 N. Bublies	
---	---	--